

SEAMING TAPE LMP

INTRODUCTION

Seaming Tape LMP is a specially constructed tape for use with the recommended Multipurpose adhesive in forming strong bonds when seam jointing artificial grass carpets used in the surfacing of sports areas.

The tape consists of a strong geo textile fabric on one side and this is laminated to a polyolefinic film to prevent the penetration of adhesive through to the under surface.

FEATURES

- Used for medium to long pile carpet seam joints.
- Impervious to moisture ingress from the base.
- Strong rot proof geo-textile bonding medium.
- Lays flat to substrate when rolled out.
- Sealed back to prevent adhesive penetrating to base.

METHOD OF USE

IMPORTANT: Before embarking on any work involving Seaming Tape LMP the Health and Safety Data Sheet should be carefully studied by those carrying out the work.

APPLICATION

Seaming Tape LMP is designed for use with Multipurpose polyurethane adhesives. It is constructed to form strong bonds to medium or long pile artificial grass carpets when used with these adhesives. The correct amount of adhesive is applied by notched applicator to the fabric side of the tape and the edges of the carpet are pressed into the wet adhesive.

For more detailed instructions on the use of this product see the Data Sheet for Multi Purpose Adhesive.

PRODUCT CHARACTERISTICS

Colour & Form: White geo textile/transparent film laminate.

Bonding Medium: Non-woven polyester geo textile.

Backing Medium: Modified Polyolefin film.

Roll Size: Length: 300 m.

Width: 30 cm, 40 cm and 50 cm.

(Other widths slit to order)

Thickness: 0.50 - 0.54 mm.

Weight: 170 g/m².

Tensile Strength: 400 N/5 cm.

Temperature Stability: -25°C to +70°C.

Storage: 0 to 30°C.

Packaging: Rolls individually film wrapped, and palletized for transport.

This leaflet is for general guidance only and may contain inappropriate information under particular conditions of use. The company cannot accept any responsibility for loss or damage that may result from the use of this information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.